

Chemical	Concentration (%)	Temp.		PVC	CPVC	PP	PVDF	TEFLON	VITON	EPDM	NITRILE	Chemical	Concentration (%)	Temp.		PVC	CPVC	PP	PVDF	TEFLON	VITON	EPDM	NITRILE												
		°C	°F											°C	°F																				
Mercuric Sulfate HgSO ₄	Satu	20	68	A	A	A	A	A	A	A	A	Methyl Chloride CH ₃ Cl		20	68	X		C	A	A	C	B	X												
		40	104	A	A	A	A	A	A	A	A																								
		60	140	A	A	A	A	A	A	A	A																								
		80	176		A																														
		100	212					A	A	A																									
		120	248					A	A																										
Mercurous Nitrate Hg ₂ (NO ₃) ₂	Satu	20	68	A		A	A	A	A	A	A	Methyl Chloroform CH ₂ Cl ₂		20	68	X		C	A	A	B	X	X												
		40	104	A			A	A																											
		60	140	A			A	A																											
		80	176				A	A																											
		100	212				A	A																											
		120	248				A	A																											
Mercury Hg		20	68	A	A	A	A	A	A	A	A	Methyl Ethyl Ketone (MEK) CH ₃ -CO-C ₂ H ₅		20	68	X	X	A	X	A	X	B	X												
		40	104	A	A	A	A	A	A	A	A																								
		60	140	A	A	A	A	A	A	A	A																								
		80	176		A	A	A	A	A	A	A																								
		100	212				A	A																											
		120	248				A	A																											
Methane CH ₄		20	68	A	A	A	A	A	A	A	A	Methyl Formate HCOOCH ₃		20	68				A	A	X	B	X												
		40	104	A	A	A	A	A	A	A	A																								
		60	140	B	B	B	A	A	A	A	A																								
		80	176				A	A	A	B																									
		100	212				A	A	B																										
		120	248				A	A																											
Methane Sulfonic Acid CH ₃ SO ₃ H	50	20	68				A	A				Methyl Isobutyl Carbinol (CH ₃) ₂ CHCH ₂ CH -(OH)CH ₃		20	68			A	A	A															
		40	104				A	A																											
		60	140				A	A																											
		80	176				A	A																											
		100	212				A	A																											
		120	248				A	A																											
Methyl Acetate CH ₃ COOCH ₃	Pure	20	68	X	X	B	A	A	X	B	X	Methyl Isobutyl Ketone (CH ₃) ₂ CHCH ₂ -COCH ₃		20	68	X	X	A	X	A	X	B	X												
		40	104				B	A		C																									
		60	140				C	A																											
		80	176				X	A																											
		100	212				A																												
		120	248				A																												
Methyl Acrylate CH ₂ CHCOOCH ₃	Pure	20	68				A	A	X	B	X	Methyl Isopropyl Ketone (CH ₃) ₂ CHCOCH ₃		20	68				X	A		X	X												
		40	104				B	A																											
		60	140				C	A																											
		80	176				X	A																											
		100	212				A																												
		120	248				A																												
Methyl Alcohol CH ₃ OH	Pure	20	68	A	A	A	A	A	B	A	A	Methyl Methacrylate CH ₂ C(CH ₃) -COOCH ₃		20	68				A	A	X	X	X												
		40	104	B	B	A	A	A	B	A	B																								
		60	140	B	B	A	A	A	C	A	C																								
		80	176			B	A	A	C	B																									
		100	212				A	A	C																										
		120	248				A	A																											
Methyl Amine CH ₃ NH ₂		20	68	X	X	B	C	A	A	A	C	Methyl Monochloroacetate ClCH ₂ COOCH ₃	Pure	20	68	C	X	A	A	A	C	A	X												
		40	104				X																												
		60	140				A																												
		80	176				A																												
		100	212				A																												
		120	248				A																												
Methyl Bromide CH ₃ Br		20	68	C		X	A	A	A	B	X	Methyl Salicylate C ₆ H ₄ (OH)COOCH ₃		20	68			A	A	A	A	X	X												
		40	104				A	A																											
		60	140				A	A																											
		80	176				A	A																											
		100	212				A																												
		120	248				A																												
Methyl Cellosolve HOCH ₂ CH ₂ OCH ₃		20	68	A		A	A	A		B		Methylene Bromide CH ₂ Br ₂		20	68				A	A	A	X	X												
		40	104				A	A																											
		60	140				A	A																											
		80	176				A	A																											
		100	212				A																												
		120	248				A																												